

Product Information

High Performance Building

Dow Corning® 121 Structural Glazing Sealant

FEATURES & BENEFITS

- Approved for structural and weatherseal applications¹
- Primerless adhesion to glass, alodine and anodized aluminum²
- Adhesion to *Dow Corning*® brand structural sealants for reglazing applications
- Adhesion and structural strength achieved in 24-48 hours
- Meets ASTM C719 Class 25 (G, A, O)
- Meets ASTM C1184 Structural Sealant Specification

COMPOSITION

- Two-part, neutral-cure, RTV silicone sealant

Fast-curing structural silicone sealant for use in structural and weatherseal applications.

APPLICATIONS

- Repair and/or replacement of structurally glazed glass and other substrates where a fast cure is required
- On-site structural glazing, including storefront systems
- Attachment of panel stiffeners where quick cure is required
- In-shop structural glazing where the use of a two-part pump is not viable

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Test	Property ³	Unit	Result
As Supplied – As Tested at 23°C (75°F) and 50% RH			
	Color – Base		Black/dark gray
	– Catalyst		White
	Physical Form		Paste
ASTM D1475	Specific Gravity – Base		1.35
	– Catalyst		1.24
As Catalyzed – Mixed at 1:1 Base to Catalyst by Volume			
	Working Time	minutes	15-45
	Unit Handling Time at 23°C (75°F), minimum ⁴	hours ³	24
	VOC Content, mixed	g/L	<25
ASTM D2202	Flow/Sag (slump)	inches (mm)	<0.2 (<5)
Cured – After 1 day at 75°F (23°C) and 50% RH			
ASTM C661	Durometer, Type A	points	30
ASTM D412	Tensile Strength	psi (MPa)	300 (2.4)
ASTM C1135	Tensile Strength at 25%	psi (MPa)	26 (0.18)
ASTM C1135	Tensile Strength, Ultimate	psi (MPa)	90 (0.62)
ASTM C1135	Elongation, Ultimate	%	25
Cured – After 7 days at 75°F (23°C) and 50% RH			
ASTM C661	Durometer, Type A	points	30-40
ASTM D412	Tensile Strength	psi (MPa)	350 (2.0)
ASTM C1135	Tensile Strength at 25%	psi (MPa)	40 (0.28)
ASTM C1135	Tensile Strength, Ultimate	psi (MPa)	135 (0.93)
ASTM C1135	Elongation, Ultimate	%	250
ASTM D 719	Movement Capability	%	±25

¹All structural glazing applications MUST be reviewed by the technical staff at Dow Corning Corporation. If their recommendations are followed, Dow Corning will issue a project-specific warranty for a specific job.

²Certain sealing materials used in the anodizing process may increase the potential for use of primer to gain adhesion within a 24-hour period. *Dow Corning*® Primer C-OS is recommended for fast and consistent adhesion, especially to *Kynar*™, polyester powdercoat and other high-performance substrates approved for architectural structural glazing applications.

³All testing was conducted using an 18-element, ½-inch diameter static mixer and a pneumatic two-part gun operating at 87 psi.

⁴Adhesion must be confirmed prior to removing temporary attachments or shipping to the job site. In general terms, glazed units can be moved or temporary attachments removed within 24 hrs depending on the temperature and relative humidity (RH). *Dow Corning*® 121 Structural Glazing Sealant can achieve the necessary strength and adhesion properties in 24 hours when applied and cured at 23°C and 50% RH. Check adhesion before moving units.

DESCRIPTION

Dow Corning[®] 121 Structural Glazing Sealant is a two-part silicone formulation designed specifically for use in structural glazing applications in field and factory applications. The material is supplied in a two-part cartridge in which the catalyst is a smooth, white paste and the base is tinted either black or gray. Once catalyzed, the material cures into a medium-modulus, flexible silicone rubber that is flexible for use in structural and weatherseal applications. It can be used in deep, narrow joints to obtain a complete cure.

Dow Corning 121 Structural Glazing Sealant cures in deep section within 24 hours and generally achieves full adhesion within 48 hours. However, full cure time depends on joint design, substrate type, temperature and humidity.

HOW TO USE

Complete design and installation guidelines are contained in the *Dow Corning Americas Technical Manual* and the *Dow Corning*[®] 121 *Structural Glazing Sealant Installation Guide* found at dowcorning.com. They must be followed for warrantable applications when using this product. Specific advice is available from your local Dow Corning representative.

Preparation

Clean all joints and glazing pockets, removing all foreign matter and contaminants such as grease, oil, dust, water, frost, surface dirt, old sealants or glazing compounds and protective coatings.

In reglazing applications where the structural sealant is performing per specification, a thin (less than 1/16 inch) layer of the existing *Dow Corning*[®] sealant should remain on the substrate. *Dow Corning* 121 Structural Glazing Sealant will achieve primerless adhesion to the cured sealant.

Application

Install backup material or joint filler, setting blocks, spacer shims, and tape. Mask areas adjacent to joints to ensure clean sealant lines.

Dow Corning 121 Structural Glazing Sealant curing agent and base must be thoroughly mixed using an airless mixing system. *Dow Corning* 121 Structural Glazing Sealant is compatible with most existing pneumatic dispensing tools that accommodate 2 x 200 mL cartridges.

The air pressure used to dispense the material should be limited to 90 psi to ensure a good mix and to prevent damage to the sealant cartridge.

Insert the cartridge into the pneumatic dispensing tool and run material out of the cartridge to ensure that both base and catalyst are at the same level. Then, attach a new static mixer to the cartridge, and the material is ready for use.

Eighteen-element, 1/2-inch diameter static mixers are included in the packaging and are required to mix the material. A new static mixer must be used for each cartridge to ensure proper mixing of the material. Neither hand-mixing nor mechanical mixing is satisfactory due to the incorporation of air, resulting in altered physical properties.

HANDLING

PRECAUTIONS

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEB SITE AT DOWCORNING.COM, OR FROM

YOUR DOW CORNING SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CORNING CUSTOMER SERVICE.

USABLE LIFE AND STORAGE

When stored in original, unopened containers in a dry location below 30°C (86°F), *Dow Corning* 121 Structural Glazing Sealant has a shelf life of 12 months from date of manufacture. Refer to product packaging for "Use By" date.

PACKAGING INFORMATION

Dow Corning 121 Structural Glazing Sealant is available in kits of 400 mL net fill (2 x 200 mL)/13.5 fl. oz. net fill (2 x 6.8 fl. oz.) cartridges.

LIMITATIONS

Dow Corning 121 Structural Glazing Sealant should not be applied:

- To building materials that bleed oils, plasticizers or solvents – materials such as impregnated wood, oil-based caulks, green or partially vulcanized rubber gaskets, and tapes
- On surfaces that will require painting or staining
- On frost-laden or wet surfaces
- In areas where abrasion and physical abuse are encountered
- In below-grade or continuous water immersion applications
- To surfaces that will be in direct contact with food

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our Web site, dowcorning.com or consult your local Dow Corning representative.

**LIMITED WARRANTY
INFORMATION – PLEASE
READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**DOW CORNING SPECIFICALLY
DISCLAIMS ANY OTHER EX-
PRESS OR IMPLIED WAR-
RANTY OF FITNESS FOR A
PARTICULAR PURPOSE OR
MERCHANTABILITY.**

**DOW CORNING DISCLAIMS
LIABILITY FOR ANY
INCIDENTAL OR
CONSEQUENTIAL DAMAGES.**

We help you invent the future.™

dowcorning.com